



SPEC-ONE 8000 Exterior Hi-Lustre (8601-8604)

SPEC-ONE 8000 Exterior Hi-Lustre provides a durable and protective finish on properly primed and prepared exterior surfaces. The Hi-Lustre finish provides outstanding gloss and color retention.

Recommended Substrates: Wood, Metal, Masonry, Hardboard, Vinyl

Application: Stir product thoroughly with a circular, lifting motion ensuring even mixing throughout. SPEC-ONE 8000 may be applied by brush, spray, pad or roller at a rate of application not to exceed 425 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 1/4" nap cover for smooth surfaces and a 3/8" or 1/2" nap cover for semi-rough surfaces. Thinning is not recommended, if necessary use water sparingly. For spray application, product may be thinned with clean water, up to 20% reduction, if necessary. Apply only when surface temperature is above 50 degrees Fahrenheit. Do not apply if rain is threatening. Avoid painting over hot surfaces or in direct sunlight.

Product Type: 100% Acrylic
Volume Solids: 33.8 ± 1.0%
Weight Solids: 47.4 ± 1.0%
Weight Per Gallon: 10.5 lbs.
Viscosity: 95 to 100 KU (Krebs Units)
Flash Point: 200°F. or greater (TT-P-141, Method 4293)
Specular Gloss: 45 to 55 units @ 60 Degrees
Light Reflectance: 90% (White or Lightest Colors)
Wet Film Thickness: 3.8 to 4.9 mils
Dry Film Thickness: 1.3 to 1.7 mils
VOC: max of 140 g/L (1.17 lbs/gal)

Dry Time: to touch = 1 hour; recoat = 4 hours; full cure = 7 to 10 days.

Thinner: Clean water.

Clean Up: Warm, soapy water.

Disposal: Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations. Do not pour down a drain or storm sewer.

The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with TSP (or equivalent) and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with three parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using an appropriate emulsifier. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. It is not necessary to dull contamination. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. **Priming:** use an appropriate primer for wood, ferrous metal, non-ferrous metal, galvanized and masonry.

Warning: Use only with adequate ventilation. Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Contains Ethylene Glycol & Crystalline Silica. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately. If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations. Obtain and read the MSDS prior to using this product. **KEEP OUT OF REACH OF CHILDREN.**