



**SPEC-PRO**  
**1000**  
**Series**

### **Spec-Pro 1000 Flat (SPC1101)**

**Spec-Pro 1000 Flat:** A professional quality flat latex wall and ceiling paint. Meets the needs of builders, painters and property managers for projects requiring excellent touch-up and hiding when applied by spray, brush and/or roll.

**Recommended Substrates:** Concrete, Concrete/Masonry Block, Gypsum Wallboard-Drywall, Plaster, Wood

**Application:** Stir thoroughly before using and occasionally during use. When using more than one container of the same color, intermix to ensure color uniformity. Use with adequate ventilation. Apply with a high quality brush, roller, by paint pad, or by spray equipment. Where necessary, apply a second coat. Airless Spray: Pressure 2000 psi, tip 0.015" or larger. Use a polyester/nylon brush, 1/2" nap roller cover. No thinning is usually required.

**Product Type:** Vinyl Acrylic Latex

**Volume Solids:** 30%  $\pm$  2%

**Weight Solids:** 51%  $\pm$  2%

**Weight Per Gallon:** 11.9 lbs.  $\pm$  0.2 lbs.

**Flash Point:** Over 200 degrees Fahrenheit

**Sheen:** Flat: 0 to 2 (60 and 85 degree gloss meter)

**Wet Film Thickness:** 4.0 mils

**Dry Film Thickness:** 1.2 mils

**VOC:** <50g/L (0.4 lbs/gal)

**Dry Time:** to touch = 30 minutes to 1 hour; recoat = 4 hours; full cure = 30 days. Dry time @ 77 degrees Fahrenheit; 50% relative humidity.

**Clean Up:** Warm, soapy water.

**Disposal:** Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations. Do not pour down a drain or storm sewer.

Surfaces to be coated must be dry, clean, sound and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate primer. Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering lightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion. Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime prior to painting the substrate. Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting.

**Warning:** Use only with adequate ventilation. Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. If you scrape, sand or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.

If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

Obtain and read the MSDS prior to using this product. **KEEP OUT OF REACH OF CHILDREN.**